

HempLime/HES-mix application data sheet



Area of Application	Metric (European)				Imperial (USA)			
	Wet Density	Dry Density	R-Value (Europe)	m3 Yield / mix	Wet Density	Dry Density	R-Value (USA)	yd3 Yield / mix
HES-mix Walls (20-35cm)	527 kg/m3	286 kg/m3	0.2/cm	0.2 m3	888 lb/yd3	480 lb/yd3	2.8/inch	0.26 yd3
HES-mix Roof (25-30cm)	305 kg/m3	160 kg/m3	0.24/cm	0.3 m3	514 lb/yd3	269 lb/yd3	3.4/inch	0.4 yd3
HES-mix Floor (+ 20% sand)	572 kg/m3	338 kg/m3	0.18/cm	0.2 m3	965 lb/yd3	570 lb/yd3	2.6/inch	0.25 yd3
HES-wall Interior Liner 2-3cm	592 kg/m3	446 kg/m3	0.015/cm	0.2 m3	999 lb/yd3	752 lb/yd3	0.2 /inch	0.25 yd3